

Lanthanum On The Tie, Found In 337 Different Particles In 119 Configurations (50 Most Common)										
Overall Rank	1st	2nd	3rd	4th	1st Avg Wt	2nd Avg Wt	3rd Avg Wt	4th Avg Wt	5th+ Avg Wt	Number
595	Ce	La	Ni	Si	65%	28%	4%	2%	2%	28
674	Ce	La	Ni	P	63%	30%	3%	2%	2%	24
772	Ce	La	Ni	Al	65%	30%	3%	2%	1%	20
827	Ce	La	Ni	Ca	64%	30%	3%	2%	2%	18
900	Ce	La	Fe	Ni	60%	26%	11%	2%	1%	16
999	Ce	Fe	La	Ni	50%	31%	13%	3%	3%	14
1172	Ce	La	Ni	S	63%	28%	4%	2%	3%	11
1608	Ce	La	Al	Ni	64%	25%	6%	3%	2%	7
1609	Ce	La	Si	Ni	58%	23%	9%	4%	6%	7
1667	Si	Al	Ce	La	46%	24%	11%	8%	11%	7
1788	Ce	La	Ca	Al	66%	22%	7%	2%	2%	6
1789	Ce	La	Ca	Ni	57%	30%	4%	3%	5%	6
2040	Ce	La	Fe	Si	53%	25%	12%	4%	6%	5
2041	Ce	La	Si	Ca	56%	30%	6%	3%	5%	5
2355	Ce	Fe	La	Al	52%	34%	9%	2%	3%	4
2356	Ce	Fe	La	Si	48%	26%	17%	3%	6%	4
2359	Ce	La	Ni	Fe	58%	28%	4%	3%	7%	4
2360	Ce	La	Pd	Al	59%	29%	7%	3%	1%	4
2361	Ce	La	S	Ni	48%	23%	7%	5%	16%	4
2413	Fe	Ce	La	Ni	60%	26%	7%	3%	4%	4
2414	Fe	Ce	La	Si	64%	22%	8%	3%	3%	4
2807	Ce	Fe	Ca	La	47%	34%	8%	5%	6%	3
2808	Ce	Fe	La	Ca	53%	30%	14%	1%	2%	3
2811	Ce	La	Al		66%	33%	1%	0%	0%	3
2812	Ce	La	Ni	Cl	58%	29%	4%	3%	5%	3
2813	Ce	La	Ni	K	62%	34%	3%	1%	1%	3
2814	Ce	La	P	Ca	58%	28%	4%	4%	6%	3
2815	Ce	La	P	Ni	56%	23%	13%	4%	4%	3
2816	Ce	La	Si	S	49%	22%	9%	7%	13%	3
2817	Ce	Si	La	Al	38%	24%	14%	9%	16%	3
2905	Fe	Ce	La	Ca	49%	28%	8%	5%	10%	3
3331	Al	P	Ce	La	33%	24%	16%	11%	15%	2
3611	Ce	Al	La	Ni	46%	30%	19%	3%	2%	2
3615	Ce	Fe	La	S	47%	38%	11%	1%	2%	2
3621	Ce	La	Ba	Ni	51%	32%	9%	4%	5%	2
3622	Ce	La	Ca	S	56%	25%	6%	4%	10%	2
3623	Ce	La	Ca	Si	52%	36%	4%	3%	5%	2
3624	Ce	La	Cl	Al	66%	30%	2%	1%	1%	2
3625	Ce	La	Fe	Al	55%	27%	12%	5%	3%	2
3626	Ce	La	Fe	S	43%	18%	10%	7%	22%	2
3627	Ce	La	P	Si	61%	21%	8%	3%	7%	2
3628	Ce	La	S	Si	46%	30%	7%	4%	13%	2
3629	Ce	La	Si	Al	47%	22%	9%	7%	15%	2
3630	Ce	La	Si	Mg	50%	20%	10%	8%	13%	2
3631	Ce	La	Si	P	62%	29%	5%	2%	3%	2
3632	Ce	La	Si		69%	30%	1%	0%	0%	2
3633	Ce	La	Ti	Si	61%	21%	7%	4%	8%	2
3978	La	Ce	Ni	P	50%	45%	2%	2%	1%	2
4588	Al	Ce	P	La	27%	26%	24%	10%	13%	1
4713	Al	P	Ca	La	37%	29%	10%	8%	16%	1